

RUBY 70



Nature - Light Raspberry, Raspberry and Orange Red
Nature



Middle Grege	Light Grege	Warm Medium Grey	Cold Dark Grey	Cold Light Grey
Cold Grey	Black	Yellow	Sand	Cold Medium Grey
Tomato	Fresh Blue	Dark Grege	Dark Blue	Light Raspberry
Raspberry	Lilac	Royal Purple	Spring Green	Turquoise

TECHNICAL DATA	STANDARDS	RUBY 70	RUBY 70 Acoustic
Classification			
Type of floor covering	ISO 10582	Heterogeneous Compact Vinyl	Resilient floor covering - Polyvinyl chloride floor covering with foam layer
Classification	ISO 10874 (EN 685) commercial industrial	Classes: 34 43	Classes: 34 42
Characteristics			
Total thickness	ISO 24346 (EN 428)	2.00mm	3.00mm
Wear layer thickness	ISO 24340 (EN 429)	0.70mm	0.70mm
Total weight	ISO 23997 (EN 430)	3 000g/m ²	2 500g/m ²
PU treatment	-	TopClean™	TopClean™
Wear layer binder content	ISO 10582	Type I	Type I
Technical performance			
Residual indentation	Average measured value	0.02mm	0.11mm
	ISO 24343-1 (EN 433) requirement	≤ 0.10mm	≤ 0.20mm
Reaction to fire	EN 13501-1	B _{fl} -s1 Glued on derivative wood panel	C _{fl} -s1 glued on derivative wood panel
Slip resistance	DIN 51130 EN 13893	R10 μ ≥ 0.30	R9 μ ≥ 0.30
Dimensional stability	ISO 23999 (EN 434)	≤ 0.10%	≤ 0.10%
Furniture leg	EN 424	No damage	No damage
Castor wheel test	ISO 4918 (EN 425)	No damage	No damage
Curl resultant to heat	ISO 23999 (EN 434)	≤ 8mm	≤ 8mm
Electrostatic properties	EN 1815 EN 1081	≤ 2kV on concrete R1 > 10 ⁹ ohms	≤ 2kV on concrete R1 > 10 ⁹ ohms
Chemical resistance	ISO 26987 (EN 423)	High resistance	High resistance
Hygiene	-	Does not contribute to infection spreading	Does not contribute to infection spreading
Thermal resistance Underfloor heating	EN ISO 10456	0.02m ² K/W Suitable	0.04m ² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6	≥ 6
Impact Sound Resistance	Standards EN ISO 10140-3 EN ISO 717/2	ΔLw = 5dB	ΔLw = 19dB

The above information is subject to modifications for the benefit of further improvement (02/2017).
For more detailed technical information, please contact Tarkett.

Royal Blue	Cognac
Orange Red	

RUBY 70 Nature

Main Product Features

- Resistance and a safety touch
- Excellent resistance to indentation and abrasion
- Superior anti slip resistance (R10)
- Available in 2 and 4 meter widths

Surface Treatment



Sustainability Tag

RUBY 70

100% Recyclable Recycled content

31% Recycled content

PHthalate FREE Technology

Better Indoor Air Quality

≤ 100 μg/m³

*TVOC AT 28 DAYS

RUBY 70 Acoustic

100% Recyclable Recycled content

31% Recycled content

Better Indoor Air Quality

≤ 100 μg/m³

*TVOC AT 28 DAYS

Logistics Information

Available in rolls:
2m & 4m
Rolls length: 231m

Laying direction:

General Information

RUBY 70

0131-0038-DOP-2014-10
http://professionals.tarkett.com

Manufactured by: Tarkett Luxembourg SA
L-9779 Lertzweiler - Luxembourg

EN 14041:2004

According to European Classification ISO 10874 (EN 685)

RUBY 70 Acoustic

0131-0056-DOP-2015-01
http://professionals.tarkett.com

Manufactured by: Tarkett Luxembourg SA
L-9779 Lertzweiler - Luxembourg

EN 14041:2004

According to European Classification ISO 10874 (EN 685)



RUBY 70



Faro 2 - Natural Honey



Haussmann




Natural

2509 8069
2509 9069



Dark Grey

2509 8070
2509 9070



Warm Brown

2509 8071
2509 9071

Faro 2



Natural

2509 8034
2509 9034



Anthracite

2509 8072
2509 9072

Oak



Warm Beige

2509 8073
2509 9073



Grey

2509 8036
2509 9036



Grey Beige

2509 8035
2509 9035




Middle Natural

2509 8074
2509 9074




Natural Honey

2509 8075
2509 9075



Beige

2509 8076
2509 9076



Dark Brown

2509 8077
2509 9077

TECHNICAL DATA	STANDARDS	RUBY 70
Classification		
Type of floor covering	ISO 10582	Heterogeneous Compact Vinyl
Classification	ISO 10874 (EN 685) commercial industrial	Classes: 34 43
Characteristics		
Total thickness	ISO 24346 (EN 428)	2.00mm
Wear layer thickness	ISO 24340 (EN 429)	0.70mm
Total weight	ISO 23997 (EN 430)	3 000g/m ²
PU treatment	-	TopClean™
Wear layer binder content	ISO 10582	Type I
Technical performance		
Residual indentation	Average measured value	0.02mm
	ISO 24343-1 (EN 433) requirement	≤ 0.10mm
Reaction to fire	EN 13501-1	B _f -s1 Glued on derivative wood panel
Slip resistance	DIN 51130 EN 13893	R10 μ ≥ 0.30
Dimensional stability	ISO 23999 (EN 434)	≤ 0.10%
Furniture leg	EN 424	No damage
Castor wheel test	ISO 4918 (EN 425)	No damage
Curl resultant to heat	ISO 23999 (EN 434)	≤ 8mm
Electrostatic properties	EN 1815 EN 1081	≤ 2kV on concrete R1 > 10 ⁹ ohms
Chemical resistance	ISO 26987 (EN 423)	High resistance
Hygiene	-	Does not contribute to infection spreading
Thermal resistance Underfloor heating	EN ISO 10456	0.02m ² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6
Impact Sound Resistance	Standards EN ISO 10140-3 EN ISO 717/2	ΔLw = 5dB

The above information is subject to modifications for the benefit of further improvement (02/2017). For more detailed technical information, please contact Tarkett.

Hetre Fayard



Light Natural

2509 8029
2509 9029

RUBY 70 Wood

Main Product Features

- Resistance and a safety touch
- Excellent resistance to indentation and abrasion
- Superior anti slip resistance (R10)
- Available in 2 and 4 meter widths


Surface Treatment




Sustainability Tag



Logistics Information



General Information



According to European Classification ISO 10874 (EN 685)

